

AMENDMENTS TO THE CLAIMS

Please amend the claims as shown below. A complete listing of all pending claims is shown below

1-4. Canceled

5. (Currently Amended) A copper based sintered contact material, wherein one or more intermetallic compounds, each of which comprises two or more elements selected from the group consisting of Ni, Si, Ti, Co, Al, V and P, are dispersed, and wherein the amount of said one or more intermetallic compounds is adjusted such that the total amount of said two or more elements is 0.5 to 10 [wt]% by volume.

6. (Canceled)

7. (Canceled)

8. (Previously Amended) The copper based sintered contact material according to claim 5, further containing non-metallic particles, comprised of one or more substances selected from the group consisting of oxides, carbides, nitrides and carbonitrides, in an amount ranging from 0.1% by volume or more to less than 4% by volume.

9. (Previously Amended) The copper based sintered contact material according to claim 5, wherein metal and/or alloy particles comprised of Mo, W, Cr, Co, Fe and Fe-C are dispersed in an amount of 0.5 to 5.0 wt%.

10. (Previously Amended) The copper based sintered contact material according to claim 5, containing 1 wt% or less MnS and/or 1 wt% or less graphite.

11. (Original) The copper based sintered contact material according to claim 10, wherein the average particle diameter of said MnS and/or graphite ranges from 20 to 200 μm or less.

12. (Currently Amended) The copper based sintered contact material according to claim 5, containing [at least 1 to 16 wt% Sn and 0 to] 25 wt% or less Pb.

13. (Previously Amended) The copper based sintered contact material according to claim 5, further containing 12 to 16 wt% Sn and a Cu-Sn compound phase which is dispersedly precipitated in the structure thereof.

14. (Currently Amended) The copper based sintered contact material according to claim 12 or 13, further containing one or more alloy elements selected from the group consisting of [An] Zn, Mn, Be, Mg, Ag, and Bi, and a solid lubricant such as MoS_2 , CaF_2 and WS_2 .

15. (Previously Amended) A double-layered sintered contact member produced by sinter bonding the copper based sintered contact material of claim 5 to an iron based material.

16. (Previously Amended) A double-layered sintered contact member according to claim 15,

which is produced by sinter bonding a pressed compact, formed from a sintered contact material containing Sn and/or Pb, to an iron based material, and

wherein the sintered compact sinter bonded to the iron based material contains 0.1 to 2 wt% one or more elements selected from the group consisting of Cr, Si, Al, P and Ti which have more significant affinity with respect to iron than with respect to copper and stabilize the α phase of iron more than the γ phase of iron.

17. (Previously Amended) A double-layered sintered contact member according to claim 15, containing Si, Al, Ti and Cr which expand a sintered layer and/or one kind of non-metallic particles which restrains a shrinkage of a sintered layer, for fear that when using the double-layered sintered contact member which has been produced through a process in which a mixed powder having a sintered contact material composition and containing Sn and/or Pb is dispersed onto a steel plate, subjected to first sinter bonding at 810°C or more, and then subjected to second sintering by mechanically increasing the density of the sintered dispersed powder layer, the layer of the mixed powder dispersed in the first sintering might peel off the steel plate owing to sinter shrinkage.

18. (Previously Amended) A double-layered sintered contact member according to claim 17, wherein Sn is added by utilizing a Cu-Sn based alloy powder containing Sn in an amount no less than Cu - 30 wt% Sn and/or Sn primary powder, so that the sintered layer in the first sintering is expanded.

19. (Currently Amended) The copper based sintered contact material according to claim 5, further containing 12 to 16 wt% Sn and a Cu-Sn compound phase which is dispersedly precipitated in the structure thereof, further containing one or more alloy elements selected from the group consisting of [An] Zn, Mn, Be, Mg, Ag, and Bi, and a solid lubricant such as MoS₂, CaF₂ and WS₂.